

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

CLAIMS

5

1. A flash memory device, characterized by:
a silicon substrate,
a first electrode formed on said silicon
substrate with an insulation film interposed
10 therebetween, and

a second electrode formed on said first
electrode with an inter-electrode insulation film
interposed therebetween,

said inter-electrode insulation film having
15 a stacked structure including at least one silicon
oxide film and one silicon nitride film, at least a
part of said silicon oxide film containing Kr with a
surface density of 10^{10}cm^{-2} or more.

20

2. A flash memory device as claimed in
claim 1, characterized in that said first electrode
25 includes a polysilicon film on a surface thereof, and
wherein said inter-electrode insulation film has a
stacked structure in which a first silicon nitride
film, a first silicon oxide film, a second silicon
nitride film and a second silicon oxide film are
30 stacked consecutively.

3. A flash memory device as claimed in claim 1, characterized in that said first electrode includes a polysilicon film on a surface thereof, and wherein said inter-electrode insulation film is
5 formed of three layers of a silicon oxide film, a silicon nitride film and a silicon oxide film.

10

4. A flash memory device as claimed in claim 1, characterized in that said first electrode includes a polysilicon film on a surface thereof, and wherein said inter-electrode film is formed of two
15 layers of a first silicon nitride film and a second silicon oxide film.

20

5. A method of fabricating a flash memory device, said flash memory device comprising a silicon substrate, a first electrode formed on said silicon substrate with an insulation film interposed
25 therebetween, and a second electrode formed on said first electrode with an inter-electrode insulation film interposed therebetween, said inter-electrode insulation film having a stacked structure including therein at least one silicon oxide film and one
30 silicon nitride film,

characterized in that said silicon oxide film is formed by a process comprising the steps of: supplying a gas containing oxygen and a gas

predominantly of Kr into a processing chamber, and exciting plasma in said processing chamber by a microwave.

5

6. A method of fabricating a flash memory device, said flash memory device comprising a silicon substrate, a first electrode formed on said silicon substrate with an insulation film interposed therebetween, and a second electrode formed on said first electrode with an inter-electrode insulation film interposed therebetween, said inter-electrode insulation film having a stacked structure in which a first silicon nitride film, a first silicon oxide film, a second silicon nitride film and a second silicon oxide film are stacked consecutively, said first electrode having a polysilicon surface, characterized in that said first and second silicon oxide films are formed by a process comprising the steps of: introducing a gas containing oxygen and a gas predominantly of Kr into a processing chamber, and exciting plasma in said processing chamber by a microwave.

7. A method of fabricating a flash memory device, said flash memory device comprising a silicon substrate, a first electrode formed on said silicon substrate with an insulation film interposed

therebetween, and a second electrode formed on said first electrode with an inter-electrode insulation film interposed therebetween, said inter-electrode insulation film having a stacked structure in which a first silicon oxide film, a silicon nitride film and a second silicon oxide film are stacked consecutively, said first electrode having a polysilicon surface, characterized in that said first and second silicon oxide films are formed by a process comprising the steps of: introducing a gas containing oxygen and a gas predominantly of Kr into a processing chamber, and exciting plasma in said processing chamber by a microwave.

15

8. A method of fabricating a flash memory device, said flash memory device comprising a silicon substrate, a first electrode formed on said silicon substrate with an insulation film interposed therebetween, and a second electrode formed on said first electrode with an inter-electrode insulation film interposed therebetween, said inter-electrode insulation film having a two-layer structure in which a silicon oxide film and a silicon nitride film are stacked consecutively, said first electrode having a polysilicon surface,

characterized in that said silicon oxide film are formed by a process comprising the steps of: introducing a gas containing oxygen and a gas predominantly of Kr into a processing chamber, and exciting plasma in said processing chamber by a

30

microwave.

5

9. A method of fabricating a flash memory device, said flash memory device comprising a silicon substrate, a first electrode formed on said silicon substrate with an insulation film interposed
10 therebetween, and a second electrode formed on said first electrode with an inter-electrode insulation film interposed therebetween, said inter-electrode insulation film having a stacked structure including at least one silicon oxide film and at least one
15 silicon nitride film,

characterized in that said silicon oxide film is formed by a process comprising the step of: exposing a silicon oxide film deposited by a CVD process to atomic state oxygen O^* formed by microwave
20 excitation of plasma in a mixed gas of an oxygen-containing gas and an inert gas predominantly of a Kr gas.

25

10. A fabrication process of a flash memory device, said flash memory device comprising a silicon substrate, a first electrode formed on said silicon
30 substrate with an insulation film interposed therebetween, and a second electrode formed on said first electrode with an inter-electrode insulation film interposed therebetween, said inter-electrode

insulation film having a stacked structure in which a first silicon nitride film, a first silicon oxide film, a second silicon nitride film and a second silicon oxide film are stacked consecutively, said
5 first electrode having a polysilicon surface,

characterized in that said first and second silicon oxide films are formed by a process comprising the step of: exposing a silicon oxide film deposited by a CVD process to atomic state oxygen O*
10 formed by exciting plasma in a mixed gas of a gas containing oxygen and a gas predominantly of a Kr gas, by a microwave.

15

11. A method of fabricating a flash memory device, said flash memory device comprising a silicon substrate, a first electrode formed on said silicon substrate with an insulation film interposed
20 therebetween, and a second electrode formed on said first electrode with an inter-electrode insulation film interposed therebetween, said inter-electrode insulation film having a stacked structure in which a first silicon oxide film, a silicon nitride film and
25 a second silicon oxide film are stacked consecutively, said first electrode having a polysilicon surface,

characterized in that said second silicon oxide film are formed by a process comprising the
30 step of: exposing a silicon oxide film deposited by a CVD process to atomic state oxygen O* formed by exciting plasma in a mixed gas of a gas containing oxygen and a gas predominantly of a Kr gas by a

microwave.

5

12. A method of fabricating a flash memory device, said flash memory device comprising a silicon substrate, a first electrode formed on said silicon substrate with an insulation film interposed
10 therebetween, and a second electrode formed on said first electrode with an inter-electrode insulation film interposed therebetween, said inter-electrode insulation film having a stacked structure including at least one silicon oxide film and at least one
15 silicon nitride film,

characterized in that said silicon nitride film are formed by a process comprising the steps of: introducing a gas containing any of an NH_3 gas or an N_2 gas and an H_2 gas and a gas predominantly of an Ar
20 gas or a Kr gas into a processing chamber, and exciting plasma in said processing chamber by a microwave.

25

13. A method of fabricating a flash memory device, said flash memory device comprising a silicon substrate, a first electrode formed on said silicon
30 substrate with an insulation film interposed therebetween, and a second electrode formed on said first electrode with an inter-electrode insulation film interposed therebetween, said inter-electrode

insulation film having a stacked structure in which a first silicon nitride film, a first silicon oxide film, a second silicon nitride film and a second silicon oxide film are stacked consecutively, said
5 first electrode having a polysilicon surface,

characterized in that said first and second silicon nitride films are formed by a process comprising the steps of: introducing an NH_3 gas or a gas containing N_2 and H_2 and a gas predominantly of
10 an Ar gas or a Kr gas into a processing chamber, and exciting plasma in said processing chamber by a microwave.

15

14. A method of fabricating a flash memory device, said flash memory device comprising a silicon substrate, a first electrode formed on said silicon
20 substrate with an insulation film interposed therebetween, and a second electrode formed on said first electrode with an inter-electrode insulation film interposed therebetween, said inter-electrode insulation film having a stacked structure in which a
25 first silicon oxide film, a silicon nitride film and a second silicon oxide film are stacked consecutively, said first electrode having a polysilicon surface,

characterized in that said silicon oxide film are formed by a process comprising the steps of:
30 introducing an NH_3 gas or a gas containing N_2 and H_2 and a gas predominantly of an Ar gas or a Kr gas into a processing chamber, and exciting plasma in said processing chamber by a microwave.

15. A method of fabricating a flash memory device, said flash memory device comprising a silicon substrate, a first electrode formed on said silicon substrate with an insulation film interposed
5 therebetween, and a second electrode formed on said first electrode with an inter-electrode insulation film interposed therebetween, said inter-electrode insulation film having a two-layer structure in which a silicon oxide film and a silicon nitride film are
10 stacked consecutively, said first electrode having a polysilicon surface,

characterized in that said silicon nitride film are formed by a process comprising the steps of: introducing an NH_3 gas or a gas containing N_2 and H_2
15 and a gas predominantly of an Ar gas or a Kr gas into a processing chamber, and exciting plasma in said processing chamber by a microwave.

20

16. A method of fabricating a flash memory device, said flash memory device comprising a silicon substrate, a first electrode formed on said silicon
25 substrate with an insulation film interposed therebetween, and a second electrode formed on said first electrode with an inter-electrode insulation film interposed therebetween, said inter-electrode insulation film having a stacked structure containing
30 at least one silicon oxide film and at least one silicon nitride film,

characterized in that said silicon nitride film is formed by a process comprising the step of:

exposing a silicon nitride film deposited by a CVD
process to hydrogen nitride radicals NH^* formed by
microwave excitation of plasma in a mixed gas of an
 NH_3 gas or a gas containing N_2 and H_2 and a gas
5 predominantly of an Ar gas or a Kr gas.

10 17. A method of fabricating a flash memory
device, said flash memory device comprising a silicon
substrate, a first electrode formed on said silicon
substrate with an insulation film interposed
therebetween, and a second electrode formed on said
15 first electrode with an inter-electrode insulation
film interposed therebetween, said inter-electrode
insulation film having a stacked structure in which a
first silicon nitride film, a first silicon oxide
film, a second silicon nitride film and a second
20 silicon oxide film are stacked consecutively, said
first electrode having a polysilicon surface,

characterized in that each of said first
and second silicon nitride films is formed by a
process comprising the step of: exposing a silicon
25 nitride film deposited by a CVD process to hydrogen
nitride radicals NH^* formed by exciting plasma in a
mixed gas of an NH_3 gas or a gas containing N_2 and H_2
and a gas predominantly of an Ar gas or a Kr gas by a
microwave.

30

18. A method of fabricating a flash memory device, said flash memory device comprising a silicon substrate, a first electrode formed on said silicon substrate with an insulation film interposed
5 therebetween, and a second electrode formed on said first electrode with an inter-electrode insulation film interposed therebetween, said first electrode having a polysilicon surface,
characterized in that said silicon nitride
10 film is formed by a process comprising the step of: exposing a silicon nitride film deposited by a CVD process to hydrogen nitride radicals NH^* formed by exciting plasma in a mixed gas of an NH_3 gas or a gas containing N_2 and H_2 and a gas predominantly of an Ar
15 gas or a Kr gas by a microwave.

20 19. A method of fabricating a flash memory device, said flash memory device comprising a silicon substrate, a first electrode formed on said silicon substrate with an insulation film interposed therebetween, and a second electrode formed on said
25 first electrode with an inter-electrode insulation film interposed therebetween, said inter-electrode insulation film having a two-layer structure in which a silicon oxide film and a silicon nitride film are stacked consecutively, said first electrode having a
30 polysilicon surface,

characterized in that said inter-electrode insulation film is formed by a process comprising the step of: exposing a silicon nitride film deposited by

a CVD process to hydrogen nitride radicals NH^* formed by exciting plasma in a mixed gas of an NH_3 gas or a gas containing N_2 and H_2 and a gas predominantly of an Ar gas or a Kr gas by a microwave.

5

20. A method of fabricating a flash memory
10 device, said flash memory device comprising a silicon substrate, a first electrode of polysilicon formed on said silicon substrate with an insulation film interposed therebetween, and a second electrode formed on said first electrode with an inter-
15 electrode oxide film interposed therebetween, characterized in that said inter-electrode oxide film is formed by a process comprising the steps of:

depositing a polysilicon film on said
20 silicon substrate as said first electrode; and exposing a surface of said polysilicon film to atomic state oxygen O^* formed by exciting plasma in a mixed gas of a gas containing oxygen and an inert gas predominantly of a Kr gas by a microwave.

25

21. A method of fabricating a flash memory
30 device, said flash memory device comprising a silicon substrate, a first electrode of polysilicon formed on said silicon substrate with an insulation film interposed therebetween, and a second electrode

formed on said first electrode with an inter-electrode nitride film,

characterized in that

said inter-electrode nitride film is formed by a
5 process comprising the steps of:

depositing a polysilicon film on said
silicon substrate as said first electrode; and

exposing a surface of said polysilicon film
to hydrogen nitride radicals NH^* formed by exciting
10 plasma in a mixed gas of a gas containing nitrogen
and hydrogen and an inert gas predominantly of a Kr
gas by a microwave.

15

22. A method of fabricating a flash memory
device, said flash memory device comprising a silicon
substrate, a first electrode of polysilicon formed on
20 said silicon substrate with an insulation film
interposed therebetween, and a second electrode
formed on said first electrode with an inter-
electrode oxynitride film interposed therebetween,
characterized in that said inter-electrode
25 oxynitride film being formed by a process comprising
the steps of:

depositing a polysilicon film on said
silicon substrate as said first electrode; and

converting a surface of said polysilicon
30 film to a silicon oxynitride film by exposing said
polysilicon film to plasma formed by exciting a mixed
gas of an inert gas predominantly of Ar or Kr and a
gas containing oxygen and nitrogen by a microwave.

23. A method of forming a silicon oxide film, characterized by the steps of:

depositing a polysilicon film on a substrate; and

5 forming a silicon oxide film on a surface of said polysilicon film by exposing the surface of said polysilicon film to atomic state oxygen O^* , said atomic state oxygen O^* being formed by exciting plasma in a mixed gas of a gas containing oxygen and
10 an inert gas predominantly of a Kr gas by a microwave.

15 24. A method of forming a silicon oxide film as claimed in claim 23, characterized in that said mixed gas is a mixture of oxygen and an inert gas predominantly of a Kr gas with a mixing ratio of 3% for oxygen and 97% for the inert gas.

20

25 25. A method of forming a silicon oxide film as claimed in claim 23, characterized in that said plasma has an electron density of 10^{12}cm^{-3} or more on said surface of said polysilicon film.

30

26. A method of forming a silicon oxide film as claimed in claim 23, characterized in that

said plasma has a plasma potential of 10 V or less at said surface of said polysilicon film.

5

27. A method of forming a silicon nitride film, characterized by the steps of:

depositing a polysilicon film on a
10 substrate; and

forming a nitride film on a surface of said polysilicon film by exposing the surface of said polysilicon film to hydrogen nitride radicals NH^* , said hydrogen nitride radicals NH^* being formed by
15 plasma that is excited in a mixed gas of a gas containing nitrogen and hydrogen as constituent elements and an inert gas predominantly of an Ar gas or a Kr gas by a microwave.

20

28. A method of forming a silicon nitride film as claimed in claim 27, characterized in that
25 said gas containing nitrogen and hydrogen is an NH_3 gas.

30

29. A method of forming a silicon nitride film as claimed in claim 27, characterized in that said mixed gas is a mixture of an NH_3 gas and an

inert gas predominantly of an Ar gas or a Kr gas with a mixing ration of 2% for said NH_3 gas and 98% for said inert gas.

5

30. A method of forming a silicon nitride film as claimed in claim 27, characterized in that
10 said gas containing nitrogen and hydrogen is a mixed gas of an N_2 gas and an H_2 gas.

15

31. A method of forming a silicon nitride film as claimed in claim 27, characterized in that said plasma has an electron density of 10^{12}cm^{-3} or more at said surface of said polysilicon film.

20

32. A method of forming a silicon nitride
25 film as claimed in claim 27, characterized in that said plasma has a plasma potential of 10 V or less at said surface of said polysilicon film.

30

33. A method of forming an oxynitride film, characterized by the steps of:

depositing a polysilicon film on a
substrate; and

converting a surface of said polysilicon
film to a silicon oxynitride film by exposing said
5 polysilicon film to plasma formed by exciting a mixed
gas of an inert gas predominantly of Ar or Kr and a
gas containing oxygen as a constituent element and a
gas containing nitrogen as a constituent element, by
a microwave.

10

34. A method of forming a silicon
15 oxynitride film as claimed in claim 33, characterized
in that said gas containing nitrogen is an NH_3 gas.

20

35. A method of forming a silicon
oxynitride film as claimed in claim 33, characterized
in that said mixed gas is a mixture of an inert gas
predominantly of Ar or Kr and an oxygen gas and an
25 NH_3 gas with a mixing ratio of 96.5% for said inert
gas and 3% for said oxygen gas and 0.5% for said NH_3
gas.

30

36. A method of forming a silicon
oxynitride film as claimed in claim 33, characterized

in that said gas containing nitrogen is a mixed gas of an N_2 gas and an H_2 gas.

5

37. A method of forming a silicon oxynitride film as claimed in claim 33, characterized in that said plasma has an electron density of 10^{12}cm^{-3} or more at said surface of said polysilicon film.

15

38. A method of forming a silicon oxynitride film as claimed in claim 33, characterized in that said plasma has a plasma potential of 10V or less at said surface of said polysilicon film.

20

39. A method of forming a silicon oxide film on a polysilicon film, characterized by the steps of:

forming plasma containing therein atomic state oxygen O^* in a processing vessel of a microwave processing apparatus, said microwave processing apparatus including, in addition to said processing vessel, a shower plate provided in a part of said processing vessel so as to extend parallel with a substrate to be processed, said shower plate including a number of apertures for supplying a

plasma gas toward said substrate to be processed, and
a microwave radiation antenna provided such that said
microwave radiation antenna emits a microwave into
said processing vessel through said shower plate,
5 said plasma being formed by supplying an inert gas
predominantly of Kr and a gas containing oxygen into
said processing vessel via said shower plate, and by
supplying a microwave into said processing vessel
from said microwave radiation antenna through said
10 shower plate; and

oxidizing, in said processing vessel, a
surface of said polysilicon film formed on said
substrate by said plasma, to form said silicon oxide
film.

15

40. A method of forming a silicon oxide
20 film as claimed in claim 39, characterized in that
said plasma has an electron density of 10^{12}cm^{-3} or
more at said surface of said polysilicon film.

25

41. A method of forming a silicon oxide
film as claimed in claim 39, characterized in that
said plasma has a plasma potential of 10V or less at
30 said surface of said polysilicon film.

42. A method of forming a silicon nitride film on a polysilicon film, characterized by the steps of:

forming plasma containing therein hydrogen
5 nitride radicals NH^* in a processing vessel of a microwave processing apparatus, said microwave processing apparatus including, in addition to said processing vessel, a shower plate provided in a part of said processing vessel so as to extend parallel
10 with a substrate to be processed, said shower plate including a number of apertures for supplying a plasma gas toward said substrate to be processed, and a microwave radiation antenna provided such that said microwave radiation antenna emits a microwave into
15 said processing vessel through said shower plate, said plasma being formed by supplying an inert gas predominantly of Ar or Kr and a gas containing nitrogen and hydrogen into said processing vessel via said shower plate, and by supplying a microwave into
20 said processing vessel from said microwave radiation antenna through said shower plate; and

nitriding, in said processing vessel, a surface of said polysilicon film formed on said substrate by said plasma, to form said silicon
25 nitride film.

30 43. A method of forming a silicon nitride film as claimed in claim 42, characterized in that said gas containing nitrogen and hydrogen is an NH_3 gas.

44. A method of forming a silicon nitride film as claimed in claim 42, characterized in that said gas containing nitrogen and hydrogen is a mixed gas of an N₂ gas and an H₂ gas.

10 45. A method of forming a silicon nitride film as claimed in claim 42, characterized in that said plasma has an electron density of 10^{12}cm^{-3} or more at said surface of said polysilicon film.

15

46. A method of forming a silicon nitride film as claimed in claim 42, characterized in that said plasma has a plasma potential of 10V or less at said surface of said polysilicon film.

25

47. A method of forming a silicon oxynitride film on a polysilicon film, characterized by the steps of:

forming plasma containing therein atomic state oxygen O* and hydrogen nitride radicals NH * in a processing vessel of a microwave processing apparatus, said microwave processing apparatus including, in addition to said processing vessel, a

30

shower plate provided in a part of said processing vessel so as to extend parallel with a substrate to be processed, said shower place including a number of apertures for supplying a plasma gas toward said
5 substrate to be processed, and a microwave radiation antenna provided such that said microwave radiation antenna emits a microwave into said processing vessel through said shower plate, said plasma being formed by supplying an inert gas predominantly of Ar or Kr
10 and a gas containing oxygen as a constituent element and a gas containing nitrogen as a constituent element into said processing vessel via said shower plate, and by supplying a microwave into said processing vessel from said microwave radiation
15 antenna through said shower plate; and

oxynitriding, in said processing vessel, a surface of said polysilicon film formed on said substrate by said plasma, to form said silicon oxynitride film.

20

48. A method of forming a silicon
25 oxynitride film as claimed in claim 47, characterized in that said gas containing nitrogen and hydrogen is an NH_3 gas.

30

49. A method of forming a silicon

oxynitride film as claimed in claim 47, characterized in that said gas containing nitrogen and hydrogen is a mixed gas of an N₂ gas and an H₂ gas.

5

50. A method of forming a silicon oxynitride film as claimed in claim 47, characterized in that said plasma has an electron density of 10^{12}cm^{-3} or more at said surface of said polysilicon film.

15

51. A method of forming a silicon oxynitride film as claimed in claim 42, characterized in that said plasma has a plasma potential of 10V or less at said surface of said polysilicon film.

20